


### Amendments to the Claims

1. (Cancelled)
2. (Cancelled)
3. (Cancelled)
4. (Withdrawn) A rubbery composition which is comprised of (1) a filler and (2) a rubbery polymer as specified in claim 2.
5. (Withdrawn) A rubbery composition as specified in claim 4 wherein the filler is selected from the group consisting of carbon black, silica, starch, and clay.
6. (Withdrawn) A rubbery composition as specified in claim 5 wherein said rubbery composition is cured.
7. (Withdrawn) A rubbery composition as specified in claim 6 wherein said rubbery composition is cured with sulfur.
8. (Withdrawn) A monomer as specified in claim 1 wherein the monomer is of the structural formula:




wherein n represents the integer 4.

9. (Cancelled)
10. (Cancelled)
11. (Withdrawn) A rubbery polymer as specified in claim 10 wherein n represents 4 or 6, and wherein m represents 4 or 6.

12. (Withdrawn) A process as specified in claim 3 wherein the polymerization is initiated with an anionic initiator.

13. (Withdrawn) A process as specified in claim 12 wherein the anionic initiator is an alkyl lithium compound.

14. (Withdrawn) A process as specified in claim 13 wherein the functionalized monomer is of the structural formula:



wherein  $n$  represents an integer from 4 to about 10.

15. (Withdrawn) A monomer as specified in claim 14 wherein  $n$  represents the integer 4.

16. (Withdrawn) A monomer as specified in claim 14 wherein  $n$  represents the integer 6.


17. (Withdrawn) A process for synthesizing an amino ethyl- $\alpha$ -methyl styrene monomer which comprises: (1) reacting diisopropenyl benzene with a cyclic amine in a reacting mixture in the presence of an alkyl lithium compound at a temperature which is within the range of  $-80^\circ\text{C}$  to  $80^\circ\text{C}$  to produce the amino ethyl- $\alpha$ -methyl styrene; and (2) deactivating the alkyl lithium compound by adding an alcohol or water to the reaction mixture containing the amino ethyl- $\alpha$ -methyl styrene.

18. (Withdrawn) A process as specified in claim 17 wherein the temperature is within the range of about -20°C to about 50°C.

19. (Withdrawn) A process as specified in claim 18 wherein the alkyl lithium compound is present at a level which is within the range of about 0.5 mole percent to about 5 mole percent, based upon the molar amount of cyclic amine present.

20. (Withdrawn) A process as specified in claim 19 wherein the cyclic amine is pyrrolidine and wherein the amino ethyl- $\alpha$ -methyl styrene monomer is 3-pyrrolidino-ethyl- $\alpha$ -methyl styrene.

21. (New) A monomer having a structural formula of:



wherein n represents an integer from 0 to about 10 and wherein m represents an integer from 0 to about 10, with the proviso that the sum of n and m is at least 4.